

# Bihoren 17 006 B

## High Density Polyethylene (HDPE) Re-granulate / Black Compound PE 100 Technical Data Sheet

### Description

Bihoren 17 006 B is a High density polyethylene re-granulate compound meeting a requirements of PE 100 produced by subsequent technological operations of separation, regrinding, blending and compounding of selected pure PE 100 pipes, technological waste. Contains 70 % of separated technological waste and 30% of prime grade HDPE PE 100 of one of Europe 's leading manufacturer.

### Application area

Bihoren 17 006 B is developed for extrusion of non pressure and pressure pipes, corrugated pipes, sheet extrusion, Does not fit to contact with food or drinking water.

### Typical colours

Bihoren 17 006 B typically offered in black.

### Typical properties

Properties	Typical Value	Unit	Test Method
Melt Flow Rate (190°C/2.16 kg)	0,5	g/10 min	ASTM D 1238
Density, 23°C	0,949	g/cm <sup>3</sup>	ASTM D 1505
Melting point (DSC)	120	°C	ASTM D 3418

### Processing

Recommended Processing Conditions 190 - 230°C  
Typical melt temperature: 160 - 180°C

### Packaging

Big bags (woven PP) on wooden pallets

### Storage and handling

Pallets should not be stored one on the top of another, risk of wetness. Hazardous in case of fall. Storage The product should be stored in a dry area with an ambient temperature. It should be kept away from sunlight, sparks, heat and flame. Inappropriate storage conditions can lead to color changes and the deterioration in physical properties. It is advised to process PE resins within 6 months after delivery.

### Recycling

Recycling The product is not hazardous or toxic and it is suitable for recycling. If it can't be recycled, the waste material can be disposed at a suitable landfill site, or at an approved waste incineration facility in accordance with applicable local, provincial, state and federal regulations. Medical Applications Policy The product mentioned herein is not tested for use in pharmaceutical/medical applications